

AMMRC TR 72-9

AD

AD 742210

STATIC AND CYCLIC FATIGUE OF CERAMIC MATERIALS


SAMUEL J. ACQUAVIVA and RICHARD CHAIT
MATERIALS TESTING DIVISION

March 1972

Approved for public release; distribution unlimited.

Reproduced by
NATIONAL TECHNICAL
INFORMATION SERVICE
Springfield, Va 22151

ARMY MATERIALS AND MECHANICS RESEARCH CENTER
Watertown, Massachusetts 02172



13

ACCOMPLISH BY	
CSSTI	WRITE SECTION <input checked="" type="checkbox"/>
NSC	TEST SECTION <input type="checkbox"/>
ORANISCHES	<input type="checkbox"/>
REPRODUCTION	
BY	
REPRODUCTION/AVAILABILITY CODES	
DATE	AVAIL. CODE/SPECIAL
A	

The findings in this report are not to be construed as an official Department of the Army position, unless so designated by other authorized documents.

Mention of any trade names or manufacturers in this report shall not be construed as advertising nor as an official indorsement or approval of such products or companies by the United States Government.

DISPOSITION INSTRUCTIONS

Destroy this report when it is no longer needed.
Do not return it to the originator.

UNCLASSIFIED
Security Classification

DOCUMENT CONTROL DATA - R & D		
(Security classification of title, body of abstract and indexing annotation must be entered when the overall report is classified)		
1. ORIGINATING ACTIVITY (Corporate author) Army Materials and Mechanics Research Center Watertown, Massachusetts 02172		2a. REPORT SECURITY CLASSIFICATION Unclassified
		2b. GROUP
3. REPORT TITLE STATIC AND CYCLIC FATIGUE OF CERAMIC MATERIALS		
4. DESCRIPTIVE NOTES (Type of report and inclusive dates)		
5. AUTHOR(S) (First name, middle initial, last name) Samuel, J. Acquaviva and Richard Chait		
8. REPORT DATE March 1972	7c. TOTAL NO OF PAGES 10	7d. NO OF SECT 9
3a. CONTRACT OR GRANT NO A. PROJECT NO D/A 1F162205AA52 01 -AMMS Code 512E.11.A52-X051801 -Agency Accession Number DA OC4808		6a. ORIGINATOR'S REPORT NUMBER(S) AMORC TR 72-9
		6b. OTHER REPORT NO(S) (Any other numbers that may be assigned this report)
10. DISTRIBUTION STATEMENT Approved for public release; distribution unlimited.		
11. SUPPLEMENTARY NOTES		12. SPONSORING MILITARY ACTIVITY U. S. Army Materiel Command Washington, D. C. 20315
13. ABSTRACT Static and cyclic fatigue characteristics were determined for two ceramic materials, an alumina AD-94 and a hot-pressed boron carbide B ₄ C. The static fatigue limits determined in three-point flexure were 23,500 psi for Al ₂ O ₃ and 43,000 psi for B ₄ C, while the cyclic fatigue limits determined by stressing a cantilevered beam were 21,700 psi for the Al ₂ O ₃ and 28,500 psi for the B ₄ C. Examination of fracture surfaces by scanning and transmission electron microscopy revealed the fracture to be of a transgranular and intergranular nature for both materials. Fracture initiated at the tension surface and propagated immediately to failure. There was no change in fracture appearance in either the static or cyclic mode of failure. (Authors)		

DD FORM 1473

REPLACES DD FORM 1473, 1 JAN 44, WHICH IS OBSOLETE FOR ARMY USE.

UNCLASSIFIED
Security Classification

14	KEY WORDS	LINK A		LINK B		LINK C	
		ROLE	WT	ROLE	WT	ROLE	WT
	Ceramic materials Alumina Boron carbide Mechanical properties Fatigue Fracture toughness Microstructure Electron microscopy						

AMMRC TR 72-9

STATIC AND CYCLIC FATIGUE OF CERAMIC MATERIALS

Technical Report by

SAMUEL J. ACQUAVIVA and RICHARD CHAIT

March 1972

D/A Project 1F162205AA52 01
AMCMS Code 512E.11.A52-XO31801
Aircraft Survivability
Agency Accession Number DA GC4808

Approved for public release; distribution unlimited.

Details of illustrations in
this document may be better
studied on microfiche

MATERIALS TESTING DIVISION
ARMY MATERIALS AND MECHANICS RESEARCH CENTER
Watertown, Massachusetts 02172

ARMY MATERIALS AND MECHANICS RESEARCH CENTER

STATIC AND CYCLIC FATIGUE OF CERAMIC MATERIALS

ABSTRACT

Static and cyclic fatigue characteristics were determined for two ceramic materials, an alumina AD-94 and a hot-pressed boron carbide B_4C . The static fatigue limits determined in three-point flexure were 23,500 psi for Al_2O_3 and 43,000 psi for B_4C , while the cyclic fatigue limits determined by stressing a cantilevered beam were 21,700 psi for the Al_2O_3 and 28,500 psi for the B_4C .

Examination of fracture surfaces by scanning and transmission electron microscopy revealed the fracture to be of a transgranular and intergranular nature for both materials. Fracture initiated at the tension surface and propagated immediately to failure. There was no change in fracture appearance in either the static or cyclic mode of failure.

INTRODUCTION


There is increased emphasis on the structural use of armor material as evidenced, for example, by the proposed Aerial Armored Reconnaissance Vehicle.^{1,2} This vehicle utilizes monocoque construction with steel armor plate serving as both the skin and primary structure. It is also possible that ceramic composite armor, i.e., ceramic facing bonded to a suitable backup material may be considered for a nonprimary but critical application, especially under severe ballistic environment. However, additional information is needed regarding the behavior of candidate materials that will serve in both a load-carrying and ballistic protection capacity. A program is underway with the objective of characterizing candidate materials. The present study covers an initial phase of this characterization of ceramic composite armor by focusing on the static and cyclic fatigue response of two candidate ceramic materials, Al_2O_3 and B_4C .

MATERIALS AND TEST PROCEDURES


Two materials were selected for investigation; (1) AD-94, a commercially available alumina Al_2O_3 , manufactured by Coors Porcelain Company, Golden, Colorado; and (2) a hot-pressed boron carbide B_4C , manufactured by the Norton Company, Worcester, Massachusetts. The microstructures of these materials are shown in Figure 1, and their properties are given in the following table:

Table I. Physical Properties

Material	Flexural Strength	Modulus	Density	Grain Size
Al_2O_3	38,000 psi	41.5×10^6 psi	3.71 g/cc	10 μ
B_4C	51,000 psi	60×10^6 psi	2.43 g/cc	10 μ



a. Alumina 94%



b. Boron Carbide

Figure 1. PHOTOMICROGRAPHS OF MATERIALS TESTED. Mag. 500X

The static fatigue tests were conducted in three-point bending with a dead-weight load suspended from the center of the specimen. The specimen size for both the static and cyclic fatigue tests was $1/4" \times 1/4" \times 3"$ with a surface finish of 10 rms.

For purposes of this study, cyclic fatigue has been defined as an intermittently applied load to a specimen such that the stress on the surface of the specimen follows a sinusoidal excursion varying from zero to a maximum tensile or compressive stress, depending on the applied load. The dynamic test consisted of applying a load at the end of a cantilevered specimen at the rate of 15 cps. The equipment utilized in this test has been described elsewhere.³

The arbitrary cut-off limit for the cyclic test was 1×10^6 cycles in the event failure did not occur. Several tests beyond this arbitrary limit were conducted; these tests indicated that a limit of 1×10^6 cycles was justified.

RESULTS AND DISCUSSION

The flexural strength of the Al_2O_3 when loaded to failure was 38,000 psi; this will be referred to as the reference strength, Figure 2. At 75% of the reference strength life was limited to 10 seconds. Decreasing the stress level to 70% or 27,000 psi increased the static fatigue life to 13-1/2 hours. At 60% of the reference strength or 23,000 psi, life was extended to 72 hours, at which time the test was terminated, it being assumed that life would be infinite at this stress level. The specimens that were not fractured in the static tests were reloaded to failure, with failure occurring at 35,000 psi or within 6 or 7%

of the reference strength, indicating that virtually no damage was incurred within the test specimen during the static test. It would thus appear that this material can be loaded statically at 60% of the reference level for an indefinite period of time.




Figure 2. STATIC FATIGUE OF CERAMIC MATERIALS

Static fatigue tests on B_4C were conducted under the same atmospheric conditions as for the Al_2O_3 , namely 72 F and 35% R.H. The reference strength of the B_4C was determined to be 51,000 psi. At 90% of this value or 46,000 psi, fracture occurred after 61 minutes; at 75% and 73% of the reference strength, static fatigue life exceeded the arbitrary limit of 72 hours. The specimens that did not fracture in the static tests were reloaded, and in each case fracture occurred at 97% of the reference strength, indicating once again that static fatigue had no detrimental effect on the strength of the material.

One of the more predominant mechanisms leading to fracture is stress corrosion,* and it is felt further tests at humidities approaching 100% and also tests conducted in a vacuum would elucidate the role of stress corrosion in fatigue. Also, additional tests to definitely establish the observed trend are planned.

Several techniques have been reported for increasing the strength of ceramic materials. Sample,⁴ for example, introduced a compressive stress on the surface of Al_2O_3 specimens by a heat treat process, and subsequent loading of the heat-treated specimens showed an increase in strength over the untreated specimens. Kirchner et al.,⁵ recognizing that failures occur at surface flaws, treated the surfaces by refiring, chemical and flame polishing, chemical etching, and glazing. These treatments also proved to be beneficial in increasing the strength of the treated material. The effect that these treatments might have on improving the fatigue life of the Al_2O_3 and B_4C should also be investigated.

The results obtained for the cyclic testing of the Al_2O_3 and B_4C are shown in Figure 3. The reference strengths for each material are the same as in the static tests. The threshold level is defined as that level of stress below which an infinite fatigue life is anticipated. The threshold level for both the Al_2O_3 and B_4C in cyclic fatigue was determined to be at 5% of the reference strength for each material. The data for Al_2O_3 compares favorably with that reported by Williams⁶ where he reports a "cyclic endurance limit of 0.56 of the single stroke strength."

Scanning electron microscopy (SEM) of the fracture surface, Figure 4, indicates fracture is of both a transgranular and intergranular nature. The location of the area shown in the micrograph is approximately at the center of the fracture surface. Transmission electron microscopy of the fracture surface of Al_2O_3 ,





Figure 3. FLEXURAL FATIGUE OF CERAMIC MATERIALS

19 066 1221 AMC 71


*Discussion with G. R. Gross, Midwest Research Institute, Kansas City, Missouri.



a. Al_2O_3 Mag. 4200X



b. B_4C Mag. 7560X



c. Al_2O_3 Mag. 1700X



d. B_4C Mag. 1525X

Figure 4. FRACTURE SURFACES BY SEM

19-066-1451/AMC-71

Figure 5 indicates that the transgranular fracture involves cleavage. It would also appear that there are some cleavage steps shown in the SEM micrograph of the B_4C , Figure 4.

Fracture mechanics concepts, based upon the Griffith criterion, were used to determine strain energy release rate and critical flaw size for the two materials. The strain energy release rate was determined by fracturing a V-notched specimen, $1/4" \times 1/4" \times 2-1/2"$, having a notch depth of 0.056 inch. The specimens were fractured in three-point bending as outlined by Davidson and Tappin⁷ who defined the strain energy release rate G by




Figure 5. FRACTURE SURFACE OF Al_2O_3 BY TEM (CARBON REPLICA) (Mag. 15,000X)

$$G = \frac{(1-\nu^2)\pi \sigma_F^2 c}{2E} \quad (1)$$

where ν is Poisson's ratio; E is Young's modulus in pounds per square inch; σ_F is the fracture stress in pounds per square inch; and c is the notch depth in inches.

Notched specimens of both Al_2O_3 and B_4C were fractured in an Instron testing machine at a crosshead speed of 0.020 inch per minute. Substituting the test data into Equation 1, the strain energy release rate for Al_2O_3 was 0.270 in-lb/sq in. (4.73×10^4 erg/cm²) and for the B_4C , 0.192 in-lb/sq in. (3.36×10^4 ergs/cm²). For the Al_2O_3 , the strain energy release rate compares favorably with 0.302 in-lb/sq in. reported by McKinney.⁸ Care should be exercised in comparing fracture energy data, since Gross and Gutschall⁹ found that the strain energy release rate was grain-size dependent.

From the Griffith criterion

$$G_c = \sigma^2 \pi a / E. \quad (2)$$

Solving Equation 2 for a , $a = (G_c E) / \sigma^2$. If σ is assumed to be the fracture stress of an unnotched bar, then it is possible to estimate the critical flaw size from Equation 2. From the test data, it was found that the critical flaw size for Al_2O_3 was 0.003 inch, approximately 75 μm or about 8 grain diameters; flaws of this size should be readily detected by nondestructive techniques. The critical flaw size for B_4C was found to be 0.0015 inch, approximately 40 μm , or about 4 grain diameters. It should be pointed out that flaws of this nature were not observed in the examination of the fracture surfaces by scanning electron microscopy. Additional tests are planned in the area of fracture energy measurements.

SUMMARY

The static and cyclic fatigue properties of two materials, an alumina AD-94 and a hot-pressed boron carbide B_4C , have been studied. The static fatigue strength of the Al_2O_3 at 72 hours was 60% of the reference strength, and for the B_4C the static fatigue for 72 hours was 74% of the reference strength. Static fatigue was determined by applying a dead-weight load to the center of a specimen of $1/4" \times 1/4" \times 3"$ dimensions; the specimen was supported at a span length of 2-1/2 inches.

The cyclic fatigue properties were determined by applying a load to the end of a cantilevered specimen. The specimen size corresponded to that used for static fatigue, with the cantilevered span being 2-1/2 inches; this ensured the stressed volume being the same for both the static and cyclic fatigue tests. The threshold level for safe cyclic fatigue conditions for both Al_2O_3 and B_4C appears to be at 57% of the reference strength level. Examination of the fracture surface revealed the fracture to be of a transgranular and intergranular nature, with the fracture initiating at the tension surface; however, no evidence was present of intermittent progressive crack propagation. This latter observation would indicate that once the crack was initiated, propagation was instantaneous.

From fracture mechanics concepts it was calculated that the strain energy release rate was 0.270 in-lb/sq in. for Al_2O_3 and 0.192 in-lb/sq in. for B_4C , and the critical flaw size was determined to be 75 μm for Al_2O_3 and 40 μm for B_4C .

LITERATURE CITED

1. *AAPIV Developed by Sikorsky Aircraft, Vertiflight*, v. 16, December 1970, p. 53.
2. WONG, A. K., and BERMAN, I. *Lightweight Ceramic Armor - A Review*. Army Materials and Mechanics Research Center, AMMRC MS 71-1, April 1971.
3. ACQUAVIVA, S. J. *A Method for Fatigue Testing Ceramic Materials*. Review of Scientific Instruments, December 1971.
4. SEMPLE, C. W. *Residual Stress Determination in Aluminum Bodies*. Army Materials and Mechanics Research Center, AMMRC TR 70-1., August 1970.
5. KIRCHNER, H. P., CRUVER, R. M., and WALKER, R. E. *Strength Effects Resulting from Simple Surface Treatment*. Presented at Symposium on the Science of Ceramic Machining and Surface Finishing, NBS, November 2-4, 1970. To be published.
6. WILLIAMS, L. S. *Fatigue and Tensiles in Mechanical Properties of Engineering Ceramics*. W. Worth Kriegel and Hayne Palmour III, ed., Interscience Publication, New York - London, 1960, p. 245-302.
7. DAVIDGE, R. W., and TAPPIN, G. *The Effective Surface Energy of Brittle Materials*. Journal of Material Science, v. 3, 1968, p. 165-175.
8. MCKINNEY, K. R. *Fracture Toughness of Ceramic Materials Using the Single-Edge-Notched Specimen*. NRL Memorandum Report 1931, September 1968.
9. BROSS, G. E., and GUTSHALL, P. L. *Fracture Energy Measurements in Structural Ceramics and Design*. S. J. Acquaviva and S. A. Bortz, ed., Gordon and Breach, New York, 1969, p. 149-163.